

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

**EP 0 694 573 A2**

(12)

**EUROPEAN PATENT APPLICATION**

(43) Date of publication:

31.01.1996 Bulletin 1996/05

(51) Int. Cl.<sup>6</sup>: **C08G 77/50**

(21) Application number: **95111680.5**

(22) Date of filing: **25.07.1995**

(84) Designated Contracting States:  
**DE FR GB IT**

(30) Priority: **26.07.1994 JP 193689/94**

(71) Applicant: **Dow Corning Toray Silicone Company,  
Limited  
Tokyo 103 (JP)**

(72) Inventor: **Kobayashi, Hideki,  
Dow Corning Toray  
Nihonbashi-muromachi, Chuo-ku, Tokyo 103  
(JP)**

(74) Representative: **Spott, Gottfried, Dr.  
D-80336 München (DE)**

(54) **Branched organosilicon compounds and a method for their preparation**


(57) The present invention relates to branched silicon-bonded hydrogen endblocked organosilicon compounds containing silalkylene groups and to a method for the preparation of such compounds. These organosilicon compounds are soluble in certain organic solvents and are prepared with a very high weight average molecular weight.

**EP 0 694 573 A2**

## Description

The present invention relates to branched organosilicon compounds having silalkylenesiloxane units, and to a method for their preparation.

Organosilicon compounds having silalkylenesiloxane units of the formula:



where R is a monovalent hydrocarbon group, and n is a positive, integer have been disclosed and are known to be resistant to molecular chain scission by ionic substances, such as acids or alkalis, compared to other organosilicons. Methods of making these compounds have been proposed by Izvestiya Akademii Nauk SSSR, Seriya Khimicheskaya, No. 4,739-744, April, 1971, and by JPA's 4-65428 and 4-65429.







However, in these methods, cyclic silalkylenesiloxanes, such as 2,2,6,6-tetramethyl-1-oxa-2,6-disilacyclohexane, are prepared in advance, and are then subjected to ring-opening polymerization. Thus, the polymer compounds obtained by the above methods are linear polymer compounds. There has been no prior disclosure of branched organosilicon compounds having silalkylenesiloxane units.

It is an object of this invention to introduce a method for the preparation of silicon-bonded, hydrogen-endblocked organopolysiloxanes containing silalkylenesiloxane units.

It is another object of this invention to produce much branched organosilicon compounds which are useful as defoaming additives in acid or alkali environments.

It is a further object of this invention to prepare such branched organosilicon compounds which are useful as additives in silicone rubber compositions.

The present invention relates to an organosilicon compound having a unit formula selected from:



R<sup>1</sup> is a monovalent hydrocarbon group having from 1 to 10 carbon atoms and is free of aliphatic unsaturation. R<sup>2</sup> is an alkylene group having from 2 to 10 carbon atoms; m has value of greater than zero; a has a value of greater than zero; b has a value of greater than zero; c has value of greater than zero; and d has value of greater than zero.

R<sup>1</sup> is exemplified by alkyl groups, such as methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, or decyl; fluorine-containing organic groups such as 3,3,3-trifluoropropyl, or 3,3,4,4,5,5,6,6-nonafluorohexyl; aryl groups such as phenyl, tolyl, or xylyl; or aralkyl groups such as benzyl or phenethyl. Preferably selected from methyl or phenyl.

R<sup>2</sup> is an alkylene group having from 2 to 10 carbon atoms and may be straight chain or branched. It is specifically exemplified by ethylene, methylethylene ethylethylene, propylethylene, butylethylene, propylene, butylene, 1-methylpropylene, pentylene, hexenylen, heptenylen, octenylen, nonenylen, or decenylen. It is preferably selected from ethylene propylene, butylene, and hexenylen.

In our organosilicon compounds, the number of silicon atoms in the polydiorganosiloxane units of the above formula is preferably less than 50% of the total number of silicon atoms in the branched organosilicon compounds of this invention.


In the organosilicon compounds of this invention, the (HR<sup>1</sup><sub>2</sub>SiO<sub>1/2</sub>) unit is the endblocking group, and the (O<sub>1/2</sub>R<sup>1</sup><sub>2</sub>SiR<sup>2</sup>R<sup>1</sup><sub>2</sub>SiO<sub>1/2</sub>) unit is a unit comprising the principal chain of the compound. Also, the (R<sup>1</sup>SiO<sub>3/2</sub>) unit and the (SiO<sub>4/2</sub>) unit are units which cause branching of the compound. At least one of these latter units must be present.

The organosilicon compounds of this invention preferably have a weight average molecular weight of 1,000 or higher, as measured by gel permeation chromatography (GPC).

Our branched organosilicon compounds are soluble in selected organic solvents, for example, aromatic hydrocarbon solvents, such as toluene or xylene; aliphatic hydrocarbon solvents, such as hexane, heptane, octane, or nonane; alicyclic hydrocarbon solvents, such as cyclohexane, cycloheptane, or cyclooctane; and fluorine-containing solvents, such as trifluoromethylbenzene, 1,3-bis(trifluoromethyl)-benzene, or methylpentafluorobenzene. In many cases, our compounds are not soluble in methanol.

The ratio of a to d and m in these organosilicon determines their solubility in selected organic solvents. The solubility and characteristics of our compounds are also determined by the type of R<sup>1</sup>, R<sup>2</sup>, and R<sup>3</sup> groups selected. Preferably, the ratio of a/b is 3 or less and the ratio of (c + d)/b is 1 or less.

Specific examples of these organosilicon compounds are compounds having their formula selected from:



wherein Me denotes methyl, Ph denotes phenyl, and a, b, c, and d have a value of greater than zero.

Our organosilicon compounds may contain the bifunctional siloxane unit, having the formula (R<sup>1</sup><sub>2</sub>SiO<sub>2/2</sub>), wherein R<sup>1</sup> is as defined above, in addition to the (HR<sup>1</sup><sub>2</sub>SiO<sub>1/2</sub>), (O<sub>1/2</sub>R<sup>1</sup><sub>2</sub>SiR<sup>3</sup>R<sup>1</sup><sub>2</sub>SiO<sub>1/2</sub>), (R<sup>1</sup>SiO<sub>3/2</sub>), and (SiO<sub>4/2</sub>) units above described.

The present invention further relates to a method of making branched organosilicon compounds, comprising (I) reacting: (A) a siloxane selected from (i) a tetrasiloxane having the formula R<sup>1</sup>Si(OR<sup>1</sup><sub>2</sub>SiH)<sub>3</sub>; (ii) a pentasiloxane having the formula Si(OR<sup>1</sup><sub>2</sub>SiH)<sub>4</sub>, or (iii) mixtures of (i) and (ii), wherein R<sup>1</sup> is a monovalent hydrocarbon group having from 1 to 10 carbon atoms and free of aliphatic unsaturation; and (B) a compound selected from the group consisting of (i) a diorganosiloxane having its formula selected from R<sup>3</sup>R<sup>1</sup><sub>2</sub>SiO(R<sup>1</sup><sub>2</sub>SiO)<sub>p</sub>SiR<sup>1</sup><sub>2</sub>R<sup>3</sup> or R<sup>3</sup>R<sup>1</sup><sub>2</sub>SiOSiR<sup>1</sup><sub>2</sub>R<sup>3</sup> wherein R<sup>1</sup> is as defined above, R<sup>3</sup> is an alkenyl group having from 2 to 10 carbon atoms, and p is an integer having a value of greater than zero; (ii) an unsaturated aliphatic hydrocarbon compound having from 3 to 10 carbon atoms and having at least 2 carbon-carbon double bonds; and (iii) an unsaturated aliphatic hydrocarbon compound having from 3 to 10 carbon atoms and having at least one carbon-carbon triple bond; in the presence of (C) a catalyst. The reactants of (I) can further comprise (D) a diorganopolysiloxane having its formula selected from HR<sup>1</sup><sub>2</sub>SiO(R<sup>1</sup><sub>2</sub>SiO)<sub>p</sub>SiR<sup>1</sup><sub>2</sub>H or HR<sup>1</sup><sub>2</sub>SiOSiR<sup>1</sup><sub>2</sub>H, wherein R<sup>1</sup> and p are as defined above.


In the present invention, the tetrasiloxanes and/or pentasiloxanes of (A) are the raw materials which supply branching to our organosilicon compounds prepared by this method. R<sup>1</sup> is as defined above including preferred embodiments thereof. Preferably R<sup>1</sup> is selected from methyl or phenyl.


Although these siloxanes provide the branched part of the organosilicon compounds of the present invention, they can also partially constitute the principal chain or an endblocking group. These tetrasiloxanes and pentasiloxanes are used individually, or a mixture of the two can be used.

The tetrasiloxane of (A) is preferably selected from MeSi(OMe<sub>2</sub>SiH)<sub>3</sub>, MeSi(OMeEtSiH)<sub>3</sub>, PhSi(OMe<sub>2</sub>SiH)<sub>3</sub>, or CF<sub>3</sub>C<sub>2</sub>H<sub>4</sub>Si(OMe<sub>2</sub>SiH)<sub>3</sub>, where Et denotes ethyl and Me or Ph are defined supra. The pentasiloxane of (A) is preferably selected from Si(OMe<sub>2</sub>SiH)<sub>4</sub> or Si(OMeEtSiH)<sub>4</sub>.

Component (B) in our method comprises a part of the principal chain of our organosilicon compound. The alkenyl groups of R<sup>3</sup> are preferably selected from vinyl, allyl, butenyl, pentenyl, hexenyl, or octenyl.

The diorganosiloxane of (i) is preferably selected from CH<sub>2</sub>=CHMe<sub>2</sub>SiOMe<sub>2</sub>SiCH=CH<sub>2</sub>,





The unsaturated aliphatic hydrocarbon compounds of (ii) or (iii) are the components which introduce alkylene groups into the organosilicon compounds of this invention. The unsaturated aliphatic hydrocarbon compounds of (ii) are selected from 1,2-propadiene (allene); 1,2-butadiene; 2-methyl-1,3-butadiene (isoprene); 2,3-dimethyl-1,3-butadiene; 1,3-pentadiene; 1,4-pentadiene; 1,5-hexadiene; and 1,3-cyclohexadiene.

The unsaturated aliphatic hydrocarbon compounds of (iii) are selected from acetylene, propyne, 1-butyne, 2-butyne, 1-pentyne, 2-pentyne, 3-methyl-1-butyne, 3,3-dimethyl-1-butyne, 1-hexyne, 2-hexyne, 1-heptyne, 1-octyne, 4-octyne, 1-nonyne, 1-decyne, and 5-decyne.

The amount of component (B) is appropriately adjusted to obtain an organosilicon compound having a desired molecular weight and amount of branching. Preferably, (B) is added such that the ratio of the number of moles of alkenyl groups in (B) to the number of moles of silicon-bonded hydrogen atoms in (A) is from about 0.5:1 to 1:0.5.

Component (C) is a catalyst which promotes an addition reaction between the silicon-bonded hydrogen atoms of (A) and the alkenyl groups of (B). This catalyst is selected from platinum catalysts, rhodium catalysts, palladium catalysts, or organic peroxides. Platinum catalysts are preferred since they readily promote addition polymerization. Preferred platinum catalysts include platinum black, silica-powder-supported platinum, carbon-powder-supported platinum, chloroplatinic acid, alcohol solutions of chloroplatinic acid, a complex of platinum and vinylsiloxane, or a complex of platinum and an olefin.

The amount of (C) is not particularly limited; however, it is preferred that (C) is added in a range of from 0.1 to 500 parts by weight per one million parts of the total weight of the reactants employed in this invention.

The reaction mixture of (I) may further comprise (D) a diorganopolysiloxane. Component (D) can comprise a part of the principal chain of our organosilicon compounds. The diorganopolysiloxane of (D) is selected from  $\text{HMe}_2\text{SiOMe}_2\text{SiH}$ ,  $\text{HMeC}_2\text{H}_5\text{SiOC}_2\text{H}_5\text{MeSiH}$ ,  $\text{H}(\text{C}_2\text{H}_5)_2\text{SiO}(\text{C}_2\text{H}_5)_2\text{SiH}$ ,  $\text{HMePhSiOMePhSiH}$ ,  $\text{HMe}_2\text{SiO}(\text{Me}_2\text{SiO})_2\text{Me}_2\text{SiH}$ ,  $\text{HMe}_2\text{SiO}(\text{MePhSiO})_2\text{Me}_2\text{SiH}$ , or  $\text{HMePhSiO}(\text{Me}_2\text{SiO})_2\text{MePhSiH}$ .

In our method, the order of addition of components (A) to (C), and optionally (D), is arbitrary, and is readily determined by those skilled in the art through routine experimentation. For example, one method comprises mixing components (A), (B), and optionally (D), heating and stirring this mixture, and then gradually adding component (C) to this mixture. Another method comprises mixing components (A) and (C), heating and stirring this mixture, and then gradually adding (B) to this mixture. Similar method comprises mixing (A) and (D), heating and stirring this mixture, next adding (B), and then gradually adding (C) to the resulting mixture.

In our method an organic solvent can be used as long as the objective of the present invention is not impaired. Organosilicon compounds of higher molecular weight are manufactured by the use of organic solvents in our invention. The organic solvent can be, for example, aromatic hydrocarbon compounds, such as toluene or xylene, aliphatic hydrocarbon compounds such as hexane, heptane, octane, or nonane, alicyclic hydrocarbon compounds, such as cyclohexane, cycloheptane, or cyclooctane, or fluorine-containing aromatic hydrocarbon compounds, such as trifluoromethylbenzene, 1,3-bis(trifluoromethyl)-benzene, or methylpentafluorobenzene.

The reaction conditions for our method are not particularly limited. If the reaction is conducted at ambient atmosphere, its reaction temperature is limited by the boiling points of components (A) - (C), and optionally (D), or the boiling point of the organic solvent (if used). If the boiling points of components (A) - (C), and optionally (D), and the organic solvent (if used) are relatively low, the reaction may be carried out under pressure.

Our silicon-bonded, hydrogen-endblocked organosilicon compounds are obtained by mixing the above components such that the number of moles of silicon-bonded hydrogen atoms in (A) is larger than the number of moles of alkenyl groups in (B).

The branched organosilicon compounds of this invention are soluble in certain organic solvents, and preferably have a weight average molecular weight of 1,000 or larger. This substance usually ranges in form from a viscous liquid to a gum at room temperature.

Our branched organosilicon compounds are resistant to molecular chain scission by ionic substances, such as acids or alkali. These compounds are useful as defoaming additives in such environments. Also, these compounds are suitable as an additive for silicone rubber compositions which cure by organic peroxides, addition reactions, or condensation reactions.


Furthermore, the organosilicon compounds of the present invention are useful starting materials for preparing organosilicon compounds which are endblocked by organofunctional groups through an addition reaction with a hydrogen-silane which contains organofunctional groups. Our organosilicon compounds are also beneficial as the starting material for preparing novel composite materials of organic resin and organosilicon compounds by an addition reaction with organic resins having carbon-carbon double bond residues.

In the following Examples, the viscosity is the value measured at 25°C.

Example 1

60 grams (g) of toluene, 53.6 g of methyltris(dimethylsiloxy)silane ( $\text{MeSi}(\text{OSiMe}_2\text{H})_3$ ), and 0.5 g of 0.5% carbon-supported platinum were loaded in a reaction vessel, and heated to 60°C while being stirred slowly. Next, a mixture of 16.56 g of 1,5-hexadiene and 20 g of toluene was added into the reaction vessel. After complete addition, the resulting mixture was heated and refluxed for 2 hours. After the reaction product was cooled and filtered, the solvent was removed by distillation, and a viscous liquid was obtained. The yield of this viscous liquid was 97%. This viscous liquid was analyzed by  $^{29}\text{Si}$ , or  $^{13}\text{C}$  nuclear magnetic resonance spectral analysis (NMR), and Fourier transform infrared absorption spectra (FT-IR). From the above results, it was confirmed that this viscous liquid was an organosilicon compound having

the average unit formula:




wherein the ratio of a/b/c was 1/1/1.

By analysis of this organosilicon compound with gel permeation chromatography (GPC), it was found that its weight average molecular weight was 6,600, calibrated by polydimethylsiloxane, and the yield of said compound obtained from the peak area was 96%. Also, it was soluble in toluene and xylene.

Example 2

60 g of toluene, 53.6 g of methyltris(dimethylsiloxy)silane and 0.5 g of 0.5% carbon-supported platinum were loaded in a reaction vessel, and heated to 95°C while being stirred slowly. Next, a mixture of 39 g of 1,3-divinyltetramethyldisiloxane and 10 g of toluene was added to the reaction vessel. After addition, the resulting mixture was heated and refluxed for 2 hours. After the product was cooled and filtered, the solvent was removed by distillation, and a viscous liquid was obtained with a yield of 99%. This viscous liquid was analyzed by  $^{29}\text{Si}$ , and  $^{13}\text{C}$  NMR, and by FT-IR. From the above results, it was confirmed that this viscous liquid was an organosilicon compound having the average unit formula:




wherein the ratio of a/b/c was 1/2.3/1.

By analysis with GPC, it was found that its weight average molecular weight was 16,000 calibrated by polydimethylsiloxane, and the yield obtained from the peak area was 90%. Also, this compound was soluble in toluene and xylene.

Example 3

60 g of toluene, 49.2 g of tetrakis(dimethylsiloxy)silane, and 0.6 g of 0.5% carbon-supported platinum were loaded in a reaction vessel, and heated to 70°C while being stirred slowly. Next, a mixture of 28.4 g of 1,3-divinyltetramethyldisiloxane and 20 g of toluene was added to the reaction vessel. After addition, the resulting mixture was refluxed by heating for 3 hours. Subsequently, the reaction product was cooled and filtered, the solvent was removed by distillation, and a viscous liquid was obtained. The yield of this viscous liquid was 98%. This liquid was analyzed by  $^{29}\text{Si}$ , and  $^{13}\text{C}$  NMR, and by FT-IR. From the above results, it was confirmed that this viscous liquid was an organosilicon compound having the average unit formula:









wherein the ratio of a/b/d was 1.9/2/1.

By GPC analysis it was found that its weight average molecular weight was 8,000 calibrated by polydimethylsiloxane, and the yield obtained from the peak area was 90%. This substance was also soluble in toluene and xylene.

## Claims

1. An organosilicon compound having its unit formula selected from:



wherein R<sup>1</sup> is a monovalent hydrocarbon group having from 1 to 10 carbon atoms and free of aliphatic unsaturation, R<sup>2</sup> is an alkylene group having from 2 to 10 carbon atoms, m has value of greater than zero, a has a value of greater than zero, b has a value of greater than zero, c has value of greater than zero, and d has value of greater than zero.

2. A compound according to Claim 1, wherein the organosilicon compound is selected from a compound having its unit formula selected from the group consisting of:

(HMe<sub>2</sub>SiO<sub>1/2</sub>)<sub>a</sub>(O<sub>1/2</sub>Me<sub>2</sub>SiC<sub>6</sub>H<sub>12</sub>Me<sub>2</sub>SiO<sub>1/2</sub>)<sub>b</sub>(MeSiO<sub>3/2</sub>)<sub>c</sub>,  
 (HMe<sub>2</sub>SiO<sub>1/2</sub>)<sub>a</sub>(O<sub>1/2</sub>Me<sub>2</sub>SiC<sub>6</sub>H<sub>12</sub>Me<sub>2</sub>SiO<sub>1/2</sub>)<sub>b</sub>(SiO<sub>4/2</sub>)<sub>d</sub>,  
 (HMe<sub>2</sub>SiO<sub>1/2</sub>)<sub>a</sub>(O<sub>1/2</sub>Me<sub>2</sub>SiC<sub>2</sub>H<sub>4</sub>Me<sub>2</sub>SiO<sub>1/2</sub>)<sub>b</sub>(SiO<sub>4/2</sub>)<sub>d</sub>,  
 (HMe<sub>2</sub>SiO<sub>1/2</sub>)<sub>a</sub>(O<sub>1/2</sub>Me<sub>2</sub>SiC<sub>2</sub>H<sub>4</sub>Me<sub>2</sub>SiO<sub>1/2</sub>)<sub>b</sub>(MeSiO<sub>3/2</sub>)<sub>c</sub>,  
 (HMe<sub>2</sub>SiO<sub>1/2</sub>)<sub>a</sub>(O<sub>1/2</sub>Me<sub>2</sub>SiC<sub>2</sub>H<sub>4</sub>Me<sub>2</sub>SiO<sub>1/2</sub>)<sub>b</sub>(CF<sub>3</sub>C<sub>2</sub>H<sub>4</sub>SiO<sub>3/2</sub>)<sub>c</sub>,  
 (HMe<sub>2</sub>SiO<sub>1/2</sub>)<sub>a</sub>(O<sub>1/2</sub>MePhSiC<sub>2</sub>H<sub>4</sub>MePhSiO<sub>1/2</sub>)<sub>b</sub>(MeSiO<sub>3/2</sub>)<sub>c</sub>,  
 and  
 (HMePhSiO<sub>1/2</sub>)<sub>a</sub>(O<sub>1/2</sub>MePhSiC<sub>2</sub>H<sub>4</sub>MePhSiO<sub>1/2</sub>)<sub>b</sub>(MeSiO<sub>3/2</sub>)<sub>c</sub>,  
 wherein, Me denotes methyl, Ph denotes phenyl, and a, b, c, and d have a value of greater than zero.

3. A method of making branched organosilicon compounds, comprising:

(I) reacting:

(A) a siloxane selected from

- (i) a tetrasiloxane having the formula R<sup>1</sup>Si(OR<sup>1</sup><sub>2</sub>SiH)<sub>3</sub>,  
 (ii) a pentasiloxane having the formula Si(OR<sup>1</sup><sub>2</sub>SiH)<sub>4</sub>, and  
 (iii) mixtures of (i) or (ii)

wherein R<sup>1</sup> is a monovalent hydrocarbon group having from 1 to 10 carbon atoms and free of aliphatic unsaturation; and

(B) a compound selected from the group consisting of

- (i) a diorganosiloxane having its formula selected from R<sup>3</sup>R<sup>1</sup><sub>2</sub>SiO(R<sup>1</sup><sub>2</sub>SiO)<sub>p</sub>SiR<sup>1</sup><sub>2</sub>R<sup>3</sup> or R<sup>3</sup>R<sup>1</sup><sub>2</sub>SiO-SiR<sup>1</sup><sub>2</sub>R<sup>3</sup> wherein R<sup>1</sup> is as defined above, R<sup>3</sup> is an alkenyl group having from 2 to 10 carbon atoms, and p is an integer having a value of greater than zero,  
 (ii) an unsaturated aliphatic hydrocarbon compound having from 3 to 10 carbon atoms and having at least 2 carbon-carbon double bonds, and  
 (iii) an unsaturated aliphatic hydrocarbon compound having from 3 to 10 carbon atoms and having at least one carbon-carbon triple bond; in the presence of

(C) a catalyst selected from platinum catalysts, rhodium catalysts, palladium catalysts, or organic peroxides.

4. A method according to Claim 3, wherein the reaction mixture of (I) further comprises (D) a diorganopolysiloxane having its formula selected from HR<sup>1</sup><sub>2</sub>SiO(R<sup>1</sup><sub>2</sub>SiO)<sub>p</sub>SiR<sup>1</sup><sub>2</sub>H or HR<sup>1</sup><sub>2</sub>SiOSiR<sup>1</sup><sub>2</sub>H, wherein R<sup>1</sup> and p are as defined above.

5. A method according to Claim 3, wherein (A) is selected from MeSi(OMe<sub>2</sub>SiH)<sub>3</sub>, MeSi(OMeEtSiH)<sub>3</sub>, PhSi(OMe<sub>2</sub>SiH)<sub>3</sub>, or CF<sub>3</sub>C<sub>2</sub>H<sub>4</sub>Si(OMe<sub>2</sub>SiH)<sub>3</sub>, where Me denotes methyl, Et denotes ethyl, and Ph denotes phenyl.

6. A method according to Claim 3, wherein (A) is selected from Si(OMe<sub>2</sub>SiH)<sub>4</sub> or Si(OMeEtSiH)<sub>4</sub> wherein Me denotes methyl, and Et denotes ethyl.

7. A method according to Claim 3, wherein R<sup>3</sup> is selected from vinyl, allyl, butenyl, pentenyl, hexenyl, or octenyl.

8. A method according to Claim 3, wherein (B) is selected from CH<sub>2</sub>=CHMe<sub>2</sub>SiOMe<sub>2</sub>SiCH=CH<sub>2</sub>,

CH<sub>2</sub>=CHCH<sub>2</sub>Me<sub>2</sub>SiOMe<sub>2</sub>SiCH<sub>2</sub>CH=CH<sub>2</sub>,  
 CH<sub>2</sub>=CH(CH<sub>2</sub>)<sub>4</sub>Me<sub>2</sub>SiOMe<sub>2</sub>Si(CH<sub>2</sub>)<sub>4</sub>CH=CH<sub>2</sub>,  
 CH<sub>2</sub>=CH(C<sub>2</sub>H<sub>5</sub>)<sub>2</sub>SiO(C<sub>2</sub>H<sub>5</sub>)<sub>2</sub>SiCH=CH<sub>2</sub>,  
 CH<sub>2</sub>=CHCH<sub>2</sub>MePhSiOMePhSiCH<sub>2</sub>CH=CH<sub>2</sub>,  
 CH<sub>2</sub>=CHMe<sub>2</sub>SiO(Me<sub>2</sub>SiO)<sub>2</sub>Me<sub>2</sub>SiCH=CH<sub>2</sub>,  
 CH<sub>2</sub>=CHCH<sub>2</sub>Me<sub>2</sub>SiO(Me<sub>2</sub>SiO)<sub>2</sub>Me<sub>2</sub>SiCH<sub>2</sub>CH=CH<sub>2</sub>, or  
 CH<sub>2</sub>=CH(CH<sub>2</sub>)<sub>4</sub>Me<sub>2</sub>SiO(Me<sub>2</sub>SiO)<sub>2</sub>Me<sub>2</sub>Si(CH<sub>2</sub>)<sub>4</sub>CH=CH<sub>2</sub>, wherein  
 Me denotes methyl, and Ph denotes phenyl.



9. A method according to Claim 3, wherein (B) is selected from 1,2-propadiene; 1,2-butadiene; 2-methyl-1,3-butadiene; 2,3-dimethyl-1,3-butadiene; 1,3-pentadiene; 1,4-pentadiene, 1,5-hexadiene; and 1,3-cyclohexadiene.
- 5 10. A method according to Claim 3, wherein (B) is selected from acetylene, propyne, 1-butyne, 2-butyne, 1-pentyne, 2-pentyne, 3-methyl-1-butyne, 3,3-dimethyl-1-butyne, 1-hexyne, 2-hexyne, 1-heptyne, 1-octyne, 4-octyne, 1-nonyne, 1-decyne, and 5-decyne.
- 10 11. A method according to Claim 3, wherein the catalyst is a platinum catalyst selected from platinum black, silica-supported platinum, carbon-supported platinum, chloroplatinic acid, an alcohol solution of chloroplatinic acid, a complex of platinum and vinylsiloxane, or a complex of platinum and an olefin.
12. A method according to Claims 3 or 4, wherein the reaction mixture of (I) further comprises an organic solvent.

15

20

25

30

35

40

45

50

55

**THIS PAGE BLANK (USPTO)**

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**

**THIS PAGE BLANK (USPTO)**